

## **Colonial Collection Datasheet**

| <b>Product Description:</b> | Premium engineered hardwood flooring   |  |
|-----------------------------|--|--|
| Warranty:                   | Residential use for 25 years, and 5 years for normal indoor light commercial use |  |
|                             | from the date of purchase.   |  |
| <b>Certification</b> :      | Conformité Européenne (CE Marking)   |  |
| FloorScore Certification    |  |  |
|                             | California Air Resources Board (CARB): calCOMPlaint <sup>™</sup> Phase 2         |  |
|                             |  |  |

Size & Spec

| Dimension       | 7-1/2 in. x 6-1/3 ft. random length                   |  |  |
|-----------------|---|--|--|
|                 | 9 in. x 7 ft. random length                           |  |  |
| Thickness       | 5/8 in. (6mm wear layer)                              |  |  |
| Construction    | 2 layers engineered hardwood                          |  |  |
| Edges & Ends    | Micro bevel   |  |  |
| Color Treatment | Smoked / Stained                                      |  |  |
| Wear Finish     | UV-cured urethane                                     |  |  |
| Grade           | Rustic  |  |  |
|                 | Select & Better                                       |  |  |
| Packing         | Width 7-1/2 in.: 19.43 sq. ft./ box, 60 boxes/ pallet |  |  |
|                 | Width 9 in.: 26 sq. ft./ box, 45 boxes/ pallet        |  |  |

## Test Data

| Thickness swelling rate due to water absorption test (%) | CNS 11342  | 3%   |
|--|------------|--|
| Formaldehyde Emission Test                               | CARB ATCM  | Less than 0.05 ppm                         |
| Fire Retardant   | CNS 7614   | Ignition Time: 30 sec.                     |
|  | (A method) | After-flame time: 4.4 sec.                 |
|  |            | After-glow time: 4.4 sec.                  |
|  |            | Char distance: 5.9 cm                      |
| Contamination resistance                                 | CNS 8058   | No change on surface                       |
|  | (B method) |  |
| Impact Resistance  | CNS 2215   | No chaps, cracks, stripping and penetrate; |
| (W2-500, 100 cm)   |            | diameter of depression: 11.2mm             |
| Bending, sticking up, distortion test                    | CNS 11342  | Stick up 0.4mm without using disorder      |